

CEM I 52,5 N WHITE

White portland cement strength class of 52.5 N

White portland cement strength class of 52.5 N with a guaranteed minimum strength of 52.5 MPa after 28 days and minimum initial strength of 20.0 MPa after 2 days. The white Portland cement opens new dimensions in design and construction, excellent quality, high strength, and aesthetic appearance.

Advantages:

- for lower development of hydration heat is suitable for use in summer
- · low changes in volume
- · excellent compatibility with plastification admixtures
- · Superior quality and high durability
- Production of white or coloured concrete, plaster or mortar with suitable pigments
- · One way to achieve saturated colours, and fine surface textures
- · High strength and an unlimited formability
- · Decorative harmony and universal use

Applications:

- Dry construction mixtures
- · Interlocking pavers and patio pavers
- · Precast concrete products
- · White and coloured concrete
- · Garden architecture elements
- Chemical Building Products
- Products in combination with grey cement

Manufacturer:

· Danucem Slovensko a.s. Plant Rohoznik

Shipping options:

• bulk in tanker trucks • dispatched from: Rohožník Plant

CEM I 52.5 N	White portland	95-100 %	0 - 5 %
Product marking	Product name	Clinker	Additives

CEM I 52.5 N white complies with EN 197-1:2011. TSÚS Bratislava supervises the production.

Danucem Slovensko a.s. has established a quality management system according to EN ISO 9001:2015 and an environmental management system according to the EN ISO 14001:2015.

Technical parameters CEM I 52.5 N white

Parameter	Test method	EN 197-1: 2011	Typical value
SO ₃ content (% wt.)	EN 196-2	≤ 4.0	2.7
Cl ⁻ content (% wt.)	EN 196-2	≤ 0.1	0.01
Volume stability (mm)	EN 196-3	≤ 10	0.5
Setting time (min.)	EN 196-3	≥ 45	125
Compressive strength in 2 days (MPa)	EN 196-1	≥ 20.0	38.0
Compressive strength in 28 days (MPa)	EN 196-1	≥ 52.5	60.0

CEM I 52.5 N white meets the requirements of Decree No. 275/2004 on Reduced Cr⁶⁺ Content.

The average values given in the Product Data Sheet are purely informative and may differ from specific samples.



Contact:

For further information about sales or technical details contact, visit www.danucem.com



