

## White Portland-limestone cement strength class of 42.5 R

White Portland-limestone cement strength class of 42.5 R with a guaranteed minimum strength of 42.5 MPa after 28 days and minimum initial strength of 20.0 MPa after 2 days. The white Portland cement opens new dimensions in design and construction, excellent quality, high strength, and aesthetic appearance.

### Advantages:

- Suitable for winter use as well
- Pumpability, decreased sedimentation
- Excellent compatibility with plastification admixtures
- Superior quality and high durability
- Good initial and final strength
- Production of white or coloured concrete, plaster or mortar with suitable pigments
- High strength and an unlimited formability
- Fine surface textures
- Decorative harmony and universal use

### Applications:

- Dry construction mixtures
- Interlocking pavers and patio pavers
- Precast concrete products
- White and coloured concrete
- Garden architecture elements
- Products in combination with grey cement

### Manufacturer:

- Danucem Slovensko a.s. Plant Rohoznik

### Shipping options:

- bulk in tanker trucks • dispatched from: Rohožník Plant

Product marking	Product name	Clinker	Limestone	Additives
CEM II/A-LL 42.5 R white	White portland-limestone cement	80 - 94 %	6 - 20 %	0 - 5 %

CEM II/A-LL 42.5 R white complies with EN 197-1:2011. TSÚS Bratislava supervises the production.

Danucem Slovensko a.s. has established a quality management system according to EN ISO 9001:2015 and an environmental management system according to the EN ISO 14001:2015.

### Technical parameters CEM II/A-LL 42.5 R white

Parameter	Test method	EN 197-1: 2011	Typical value
SO <sub>3</sub> content (% wt.)	EN 196-2	≤ 4.0	2.7
Cl <sup>-</sup> content (% wt.)	EN 196-2	≤ 0.1	0.01
Volume stability (mm)	EN 196-3	≤ 10	0.5
Setting time (min.)	EN 196-3	≥ 60	125
Compressive strength in 2 days (MPa)	EN 196-1	≥ 20.0	31.0
Compressive strength in 28 days (MPa)	EN 196-1	≥ 42.5 ≤ 62.5	57.0

CEM II/A-LL 42.5 R white meets the requirements of Decree No. 275/2004 on Reduced Cr<sup>6+</sup> Content.

The average values given in the Product Data Sheet are purely informative and may differ from specific samples.



DUNAJ

DUNA

DONAU

DANUBE

Contact:  
For further information about sales or technical details  
contact, visit [www.danucem.com](http://www.danucem.com)