

# **CEM III/A 42,5 N**

## White Blast Furnace Portland-slag cement strength class of 42.5 N

White blast furnace cement strength class of 42.5 R with a guaranteed minimum strength of 42.5 MPa after 28 days and minimum initial strength of 20.0 MPa after 7 days. The white Portland cement opens new dimensions in design and construction, excellent quality, high strength, and aesthetic appearance.

#### Advantages:

- · highest quality and high durability
- excellent functionality and unrivalled appearance
- for lower development of hydration heat is suitable for use in summer
- · low changes in volume
- · excellent processability
- · excellent compatibility with plastification admixtures
- · possible to add pigments to concrete
- · high final compressive strength

#### Applications:

- · Highest quality and high durability
- Production of white or coloured concrete by suitable pigments
- Ready mix production, and production of transported concrete
- Production of plain concrete of higher strength classes and reinforced concrete structures
- · Plaster and masonry mortar

#### Manufacturer:

• Danucem Slovensko a.s. Plant Rohoznik

#### **Shipping options:**

• bulk in tanker trucks • dispatched from: Rohožník Plant

Product marking	Product name	Clinker	Blast Furnace Slag	Additives
CEM III/A 42.5 N	White Blast furnace cement	35 -64 %	36 - 65 %	0 - 5 %

CEM III/A 42.5 N white complies with EN 197-1:2011. TSÚS Bratislava supervises the production.

Danucem Slovensko a.s. has established a quality management system according to EN ISO 9001:2015 and an environmental management system according to the EN ISO 14001:2015.

### Technical parameters CEM III/A 42.5 N white

Parameter	Test method	EN 197-1: 2011	Typical value
SO <sub>3</sub> content (% wt.)	EN 196-2	≤ 4.0	2.0
Cl <sup>-</sup> content (% wt.)	EN 196-2	≤ 0.1	0.01
Volume stability (mm)	EN 196-3	≤ 10	0.8
Setting time (min.)	EN 196-3	≥ 60	160
Compressive strength in 2 days (MPa)	EN 196-1	≥ 10.0	24.0
Compressive strength in 28 days (MPa)	EN 196-1	≥ 42.5 ≤ 62.5	59.0
Whiteness (Ry)	-	-	74-77

The average values given in the Product Data Sheet are purely informative and may differ from specific samples.

CEM III/A 42.5 N white meets the requirements of Decree No. 275/2004 on Reduced Cr6+ Content.

